

GOTECH "the best partner" to raise your competition

GT-7022-3 耐升華（耐乾熱）試驗機

SCORCH TESTER

JIS-L0850, 0879, 0880, 1041, ISO-105, DIN-54060

將復合試片置於本機一定溫度之熱板間夾壓，經過一定時間取出，放置4小時後，對照灰色標，評定染色耐升華等級。本機熱板傳熱均勻，外框保溫力特強。

To compress combined specimen between heating plates with fixed temperature, taken out after some period, then set for four hours, comparing with grey scale to appraise grade of color-dyeing sublimation-endurance. The heating plate of the tester is functioned with heat-transmission averagely, the affect of keeping warmth of outer case is very strong.

型式	Model	3 Pieces
試片	Specimen	100 x 40 mm
熱板尺寸	Heat plate size	102 x 42 mm
熱板壓力	Heat plate pressure	40±10 g/cm ²
溫度	Temperature	Regular~300°C (Usually at 150,180,200°C)
體積	Dimension (WXDXH)	43x55x36 cm
重量	Weight	22 kg
電源	Power	1 f , AC 220 V



了解更多产品信息，请登录我司网站 www.gotech.biz